

Avery Dennison® SF 100-120-S Glow in the dark Calendered Vinyl

Features

- High gloss finish
- Dimensionally stable liner for easy converting
- Excellent conversion properties on computerised cutters
- Easy cutting and weeding
- Non-toxic, non-radioactive Excellent indoor durability
- Uses zero electricity

Description



Film: 202 micron special polyester



Adhesive: Clear permanent acrylic



Backing: 78# Kraft



Indoor life:
Up to 5 years, indoor only

Conversion

- | | |
|--|---|
| <input checked="" type="checkbox"/> Flat bed cutters | <input type="checkbox"/> Cold overlaminating |
| <input checked="" type="checkbox"/> Friction fed cutters | <input type="checkbox"/> Estat printing |
| <input checked="" type="checkbox"/> Die cutting | <input type="checkbox"/> Water based inkjet |
| <input type="checkbox"/> Thermal transfer | <input type="checkbox"/> Solvent inkjet |
| <input checked="" type="checkbox"/> Screen printing | <input checked="" type="checkbox"/> UV Cured inkjet |

Common Applications

- Safety Signs
- Emergency Exit
- Markings
- Evacuation Signs
- Illuminate Pathways
- Location Signs

Uses

Avery Dennison® Glow-in-the-Dark Film is a specialty photoluminescent non-coated rigid polyester film that can be used for exit and directional signs, identification of fire alarms, fire extinguishers and evacuation routes.

This product performs in accordance with ASTM 2030-06: Recommended Uses of Photoluminescent Safety Markings, meets ASTM E2072-04 Standard Specification for Photoluminescent (Phosphorescent) Safety Markings.

Physical characteristics

General

Calliper, face film	ISO 534	202 micron
Calliper, face film & adhesive	ISO 534	227 micron
Dimensional stability	DIN 30646	<0.4 mm
Tensile strength	N/a	
Elongation	N/a	
Gloss	@60 °	120
Adhesion, 24 hours		963 N/m
Adhesion, after 1 week		1094 N/m
Flammability		Self extinguishing
Shelf life	Stored at 22° C/50-55 % RH	1 years
Durability **	Indoor only	5 years unprinted

Thermal

Application temperature	Minimum: + 10°C
Temperature range	- 45°C to + 82°C

Chemical

Resistant to most mild acids, alkalis, and salt solutions.

Important

Information on physical characteristics is based upon tests we believe to be reliable. The values listed herein are typical values and are not for use in specifications. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of any material for their specific use.

All technical data is subject to change without prior notice.

Warranty

Avery Dennison® materials are manufactured under careful quality control and are warranted to be free from defect in material and workmanship. Any material shown to our satisfaction to be defective at the time of sale will be replaced without charge. Our aggregate liability to the purchaser shall in no circumstances exceed the cost of the defective materials supplied. No salesman, representative or agent is authorised to give guarantee, warranty, or make any representation contrary to the foregoing.

All Avery Dennison® materials are sold subject to the above conditions, being part of our standard conditions of sale, a copy of which is available on request.

**Durability

Durability is based on exposure conditions in the normal middle European and central North American regions. Actual performance life will depend on substrate preparation, exposure conditions and maintenance of the marking. For instance, in the case of signs facing north in the southern hemisphere or south in the northern hemisphere; in areas of long high temperature exposure such as northern Australia; in industrially polluted areas or high altitudes, exterior performance will be decreased. Please refer to Avery Dennison Instructional Bulletin 1.3 for definitions and reductions based on the 'Zone System'.

***Information unavailable at time of printing.

Test Methods

Dimensional stability:

Is measured on a 150 x 150 mm aluminium panel to which a specimen has been applied; 72 hours after application the panel is exposed for 48 hours to + 70°C, after which the shrinkage is measured.

Adhesion:

(FTM-1, FINAT) is measured by peeling a specimen at a 180° angle from a stainless steel or float glass panel, 24 hours after the specimen has been applied under standardised conditions. Initial adhesion is measured 20 minutes after application of the specimen.

Flammability:

A specimen applied to aluminium is subjected to the flame of a gas burner for 15 seconds. The film should stop burning within 15 seconds after removal from the flame.

Temperature range:

A specimen applied to stainless steel is exposed at high and low temperatures and brought back to room temperature. 1 hour after exposure the specimen is examined for any deterioration. Note: Prolonged exposure to high and low temperatures in the presence of chemicals such as solvents, acids, dyes, etc. may eventually cause deterioration.

Chemical Resistance:

All chemical tests are conducted with test panels to which a specimen has been applied. 72 hours after application the panels are immersed in the test fluid for the given test period. 1 hour after removing the panel from the fluid, the specimen is examined for any deterioration.

Corrosion Resistance:

A specimen applied to aluminium is exposed to saline mist (5% salt) at 35°C. After exposure, the film is removed and the panel is examined for traces of corrosion.



Graphics
Solutions

Avery Dennison Graphics Solutions Asia Pacific

www.graphicsap.averydennison.com