Avery Dennison® MPI 3003 PP Gloss White Promotional Vinyl Grey Permanent

Features

- Excellent printability and handling through wide format printers
- · Good outdoor durability and performance
- High gloss finish for superior appearance
- · Easy application to a wide variety of substrates
- Good dimensional stability after application
- · Excellent value for money for short term promotional graphics
- Excellent adhesion to most popular substrates
- Grey adhesive for excellent hiding properties

Description



Film: 90 micron gloss white monomeric calendered vinyl



Adhesive: Permanent grey acrylic



Backing: One side coated Kraft paper, 125g/m²



Outdoor life: Up to 3 years (unprinted)

Application surface: Flat, simple curves

Conversion⁺

	Flat bed cutters		Cold overlaminating		
	Friction fed cutters		Electrostatic printing		
	Die cutting		Latex inkjet		
	Thermal transfer		Eco solvent inkjet		
	Screen printing		Solvent inkjet		
	Offset printing		UV curable inkjet		
$^{\scriptscriptstyle +}\! \text{Always}$ test with your combination of printer and inks prior to commercial					
use	e.				

Common Applications

- Billboards
- · Real estate signs
- · Point of purchase
- Outdoor advertising
- Indoor advertising
- Exhibition
- Windows

Uses

Avery Dennison MPI 3003 PP is a gloss white promotional vinyl film with a grey adhesive designed for use in a wide range of short-term promotional and general signage applications where good outdoor durability and value for money is required.

Physical characteristics

General

ISO 534	90 micron
DIN 30646	0.5 mm max
ISO 2471	92%
FINAT FTM-1, stainless steel	480 N/m
FINAT FTM-1, stainless steel	640 N/m
	Self extinguishing
Stored at 20-25° C / 50-55 % RH	2 years
Vertical exposure ^	Up to 3 years (unprinted)
	DIN 30646 ISO 2471 FINAT FTM-1, stainless steel FINAT FTM-1, stainless steel Stored at 20-25° C / 50-55 % RH

^ See ICS Performance Guarantee Durability Bulletin for your specific printer and ink combination for further information

Thermal

Application temperature	Minimum: +10°C
Service temperature range	- 40°C to + 100°C

Chemical

Resistant to most petroleum based oils, greases and aliphatic solvents Resistant to most mild acids, alkalies, and salts

Note:

Materials have to be properly dried and cured before further processing, like laminating, varnishing, trimming, contour cutting or application. The residual solvents can otherwise change the products' specific features and properties.

Test Methods

Dimensional stability: Is measured on a 150 x 150 mm aluminium panel to which a specimen has been applied; 72 hours after application the panel is exposed for 48 hours to + 70°C, after which the shrinkage is measured.

Adhesion: (FTM-1, FINAT) is measured by peeling a specimen at a 180° angle from a stainless steel or float glass panel, 24 hours after the specimen has been applied under standardised conditions. Initial adhesion is measured 20 minutes after application of the specimen.

Flammability:
A specimen applied to aluminium is subjected to the flame of a gas burner for 15 seconds. The film should stop burning within 15 seconds after removal from the

Temperature range:A specimen applied to stainless steel is exposed at high and low temperatures and brought back to room temperature. 1 hour after exposure the specimen is examined for any deterioration. Note: Prolonged exposure to high and low temperatures in the presence of chemicals such as solvents, acids, dyes, etc. may eventually cause deterioration.

Important

Information on physical characteristics is based upon tests we believe to be reliable. The values listed herein are typical values and are not for use in specifications. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of any material for their specific

All technical data is subject to change without prior notice.

Warranty

Avery® materials are manufactured under careful quality control and are warranted to be free from defect in material and workmanship. Any material shown to our satisfaction to be defective at the time of sale will be replaced without charge. Our aggregate liability to the purchaser shall in no circumstances exceed the cost of the defective materials supplied. No salesman, representative or agent is authorised to give guarantee, warranty, or make any representation contrary to the foregoing.

All Avery® materials are sold subject to the above conditions, being part of our standard conditions of sale, a copy of which is available on request.

**Durability

Durability is based on exposure conditions in the Asia Pacific region. Actual performance life will depend on substrate preparation, exposure conditions and maintenance of the marking. For instance, in the case of signs facing north in the southern hemisphere or south in the northern hemisphere; in areas of long high temperature exposure such as northern Australia; in industrially polluted areas or high altitudes, exterior performance will be decreased.

*Compatible with most media and ink combinations. Test prior to use.

***Information unavailable at time of printing

Chemical Resistance:
All chemical tests are conducted with test panels to which a specimen has been applied. 72 hours after application the panels are immersed in the test fluid for the given test period. 1 hour after removing the panel from the fluid, the specimen is examined for any deterioration.

Corrosion Resistance:

A specimen applied to aluminium is exposed to saline mist (5% salt) at 35°C. After exposure, the film is removed and the panel is examined for traces of corrosion



Avery Dennison Graphics Solutions Asia Pacific