

Avery Dennison[®] Frosted Sparkle SLP

For Short Life Glass Decoration Applications

Features

- Excellent Sand Blast & Sparkle Effect
- Exceptional Value for Money for Short Life Promotional Graphics on Glass
- Excellent Printability on Eco-Solvent, Solvent and Latex Printers
- Good Dimensional Stability During Conversion and Application
- Good Outdoor Durability and Performance for Short Life Graphics
- Versatile Clear Removable Adhesive with Excellent Adhesion to Glass Substrates.
- Easy cutting and weeding

Description



Film: 90 Micron Translucent Monomeric Calendered Vinyl



Adhesive: Clear Removable Acrylic



Backing Options:
a) 50 micron PET liner
b) One side PE coated paper, 140 g/m²



Outdoor Durability:** Up to 1 year - Asia Pacific

Indoor Durability:** Up to 2 Years

Conversion[^]

- | | |
|---|---|
| <input type="checkbox"/> Flat bed cutters | <input type="checkbox"/> Cold overlaminating |
| <input type="checkbox"/> Friction fed cutters | <input type="checkbox"/> Electrostatic printing |
| <input type="checkbox"/> Die cutting | <input type="checkbox"/> UV curable inkjet |
| <input type="checkbox"/> Thermal transfer | <input checked="" type="checkbox"/> Eco solvent inkjet |
| <input type="checkbox"/> Screen printing | <input checked="" type="checkbox"/> Solvent inkjet |
| <input type="checkbox"/> Offset printing | <input checked="" type="checkbox"/> Latex Inkjet* |

[^]Always test with your combination of printer and inks prior to commercial use.

*Test the compatibility of the product for their converting process on Latex Printing

Common Applications

- Architectural Graphics
- Outdoor Glass Advertising
- Window Graphics
- Shop Façade's

Uses

Avery Dennison[®] Eco Frosted Sparkle Films are designed to create the Image of Sand Blasted Decorations on Glass without the Use of Physical Sand Blasting Techniques and is also suitable for functional and manifestation graphics. Avery Dennison Eco Frosted Sparkle can be applied to flat surfaces and produces Best results when applied to Transparent Substrates such as Glass and other similar transparent substrates.

Physical characteristics

General

Caliper, Face Film	ISO 534	90 micron
Caliper, Face Film & Adhesive	ISO 534	110 micron
Gloss, GU @ 85°	ISO 2813	≥ 10
Adhesion, initial	FINAT FTM-1, stainless steel	≥ 5 N/25mm
Adhesion, ultimate	FINAT FTM-1, stainless steel	≥ 6 N/25mm
Flammability		Self-extinguishing
Shelf life	Stored at 22° C/50-55 % RH	12 months from date of manufacture
Durability **		
Outdoor	Vertical Exposure	Up to 1 year (Unprinted)*
Indoor	Vertical Exposure	Up to 2 years (Unprinted)*

Thermal

Application Temperature	Minimum: +10°C
Service Temperature Range	5°C to +60°C

Chemical

Resistant to most petroleum based oils, greases and aliphatic solvents

Resistant to most mild acids, alkalies, and salts

Note:

*Solvent and Eco solvent digital printed films must be properly dried and cured before further processing, like laminating, varnishing, trimming, contour cutting or application. The residual solvents can otherwise change the products' specific features and properties.

Test Methods

Dimensional stability:

Is measured on a 150 x 150 mm aluminium panel to which a specimen has been applied; 72 hours after application the panel is exposed for 48 hours to + 70°C, after which the shrinkage is measured.

Adhesion:

(FTM-1, FINAT) is measured by peeling a specimen at a 180° angle from a stainless steel or float glass panel, 24 hours after the specimen has been applied under standardised conditions. Initial adhesion is measured 20 minutes after application of the specimen.

Flammability:

A specimen applied to aluminium is subjected to the flame of a gas burner for 15 seconds. The film should stop burning within 15 seconds after removal from the flame.

Temperature range:

A specimen applied to stainless steel is exposed at high and low temperatures and brought back to room temperature. 1 hour after exposure the specimen is examined for any deterioration. Note: Prolonged exposure to high and low temperatures in the presence of chemicals such as solvents, acids, dyes, etc. may eventually cause deterioration.

Important

Information on physical characteristics is based upon tests we believe to be reliable. The values listed herein are typical values and are not for use in specifications.

They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of any material for their specific use.

All technical data is subject to change without prior notice.

Warranty

Avery® materials are manufactured under careful quality control and are warranted to be free from defect in material and workmanship. Any material shown to our satisfaction to be defective at the time of sale will be replaced without charge. Our aggregate liability to the purchaser shall in no circumstances exceed the cost of the defective materials supplied. No salesman, representative or agent is authorised to give guarantee, warranty, or make any representation contrary to the foregoing.

All Avery® materials are sold subject to the above conditions, being part of our standard conditions of sale, a copy of which is available on request.

**Durability

Durability is based on exposure conditions in the Asia Pacific region. Actual performance life will depend on substrate preparation, exposure conditions and maintenance of the marking. For instance, in the case of signs facing north in the southern hemisphere or south in the northern hemisphere; in areas of long high temperature exposure such as northern Australia; in industrially polluted areas or high altitudes, exterior performance will be decreased.

^Compatible with most printer and ink combinations. Test with your combination of printer and inks prior to commercial use.

***Information unavailable at time of printing.

Chemical Resistance:

All chemical tests are conducted with test panels to which a specimen has been applied. 72 hours after application the panels are immersed in the test fluid for the given test period. 1 hour after removing the panel from the fluid, the specimen is examined for any deterioration.

Corrosion Resistance:

A specimen applied to aluminium is exposed to saline mist (5% salt) at 35°C. After exposure, the film is removed and the panel is examined for traces of corrosion.