NR Pro 20

Optical & Solar Properties

Ultra Violet Block	>99%
Visible Light Transmitted	22%
Visible Light Reflected (exterior)	7%
Glare Reduction	76%
SIRR	50%
IRER	37%
Shading Coefficient	0.60
Total Solar Energy Reflected	7%
Total Solar Energy Transmitted	37%
Total Solar Energy Absorbed	56%
Total Solar Energy Rejected	48%

Technology Nanotechnology UV Stable Dye

Color Tone Graphite

Construction 2-Ply Weatherable

Thickness 1.5 Mil

Color Stable Yes

Catalogue Number R058P6A



ARPANSA UPF RATING

Performance results are calculated on 1/4" (6mm) clear glass using NFRC methodology and LBNL Window 5.2 software, and are subject to variations in process conditions within industry standards

