



SF Clear 8 mil i

Mechanical Properties

Thickness	8 mil
Tensile Strength at Break	28,500 PSI
Break Strength	224 lb/inch
Elongation at Break	125 %
Peel Strength	7 lb/inch

Optical & Solar Properties

	3mm Single
Visible Light Transmitted	88%
Visible Light Reflected (interior)	11%
Visible Light Reflected (exterior)	11%
Ultra Violet Block	99%
Total Solar Energy Reflected	9%
Total Solar Energy Transmitted	80%
Total Solar Energy Absorbed	11%
Glare Reduction	2%
Shading Coefficient	0.95
Solar Heat Gain Coeff. (G-Value)	0.83
U-Value Winter (IP)	1.07
U-Value Winter (SI)	6.07
Total Solar Energy Rejected	17%

Accredited Safety Tests

Impact	AS/NZS 2208
	ANSI Z97.1 (48" pendulum fall)
	CPSC 1201 Title 16 (48" pendulum fall)
	EN 12600 Class 2B2, 1B1
Shock Tube Test	GSA: 3A, ISO: C, ASTM: Minimal Hazard

DS No 1231, April 2018