



DR OptiTune 20i

Optical & Solar Properties

	Single Pane	Double Pane
Visible Light Transmitted	21%	19%
Visible Light Reflected (interior)	15%	15%
Visible Light Reflected (exterior)	32%	35%
Ultra Violet Block	99%	99%
Total Solar Energy Reflected	31%	31%
Total Solar Energy Transmitted	18%	16%
Total Solar Energy Absorbed	51%	53%
Emissivity (Room Side)	0.80	0.80
Glare Reduction	77%	76%
Selective InfraRed Reduction (SIRR)	83%	83%
InfraRed Energy Rejection (IRER)	68%	68%
Shading Coefficient	0.38	0.51
Solar Heat Gain Coeff. (G-Value)	0.33	0.44
U-Value Winter (IP)	1.02	0.48
U-Value Winter (SI)	5.79	2.70
Luminous Efficacy	0.55	0.38
Total Solar Energy Rejected	67%	56%

R069R2W - Water Activated Adhesive



Powered by
NanoTechnology

