



# NT Natura 30i

## Optical & Solar Properties

	Single Pane	Double Pane
Visible Light Transmitted	31%	29%
Visible Light Reflected (interior)	9%	10%
Visible Light Reflected (exterior)	14%	21%
Ultra Violet Block	99%	99%
Total Solar Energy Reflected	15%	19%
Total Solar Energy Transmitted	33%	28%
Total Solar Energy Absorbed	52%	53%
Emissivity (Room Side)	0.87	0.87
Glare Reduction	65%	65%
Selective InfraRed Reduction (SIRR)	65%	65%
InfraRed Energy Rejection (IRER)	49%	49%
Shading Coefficient	0.56	0.66
Solar Heat Gain Coeff. (G-Value)	0.48	0.58
U-Value Winter (IP)	1.05	0.48
U-Value Winter (SI)	6.00	2.75
Luminous Efficacy	0.55	0.44
Total Solar Energy Rejected	52%	42%

R069L8W - Water Activated Adhesive



Powered by  
NanoTechnology

