

Avery Dennison® MPI 3111 Transit

Gloss White Promotional Clear Removable

Features

- Excellent printability on solvent and UV curable inkjet printers and screen presses
- StaFlat liner for exceptional lay flat performance during printing on wide-format screen press and drum inkjet printers
- High gloss finish for superior appearance
- High opacity for minimizing substrate colour showing through
- Very good dimensional stability after application
- Excellent low temperature adhesion performance
- Easily removed with heat for up to 1 year with little or no adhesive residue

Conversion*

- | | |
|--|---|
| <input type="checkbox"/> Flat bed cutters | <input type="checkbox"/> Cold overlaminating |
| <input type="checkbox"/> Friction fed cutters | <input type="checkbox"/> Electrostatic printing |
| <input type="checkbox"/> Die cutting | <input checked="" type="checkbox"/> Latex inkjet |
| <input type="checkbox"/> Thermal transfer | <input checked="" type="checkbox"/> Eco solvent inkjet |
| <input checked="" type="checkbox"/> Screen printing | <input checked="" type="checkbox"/> Solvent inkjet |
| <input type="checkbox"/> Offset printing | <input checked="" type="checkbox"/> UV curable inkjet |

*Always test with your combination of printer and inks prior to commercial use.

Uses

Avery Dennison® MPI 3111 Transit is a gloss white promotional film which provides exceptional lay flat performance during converting and is designed for use in a wide range of short-term promotional applications, especially transit advertising where flexible, high opacity, good outdoor durability, removability and value for money is required.

Description



Film: 90 micron gloss white high opacity monomeric calendared vinyl



Adhesive: Clear removable acrylic



Backing: Two-side PE coated StaFlat, 145 g/m²



Outdoor life: Up to 3 years (unprinted)

Application surface: Flat, simple curves

Common Applications

- Transit advertising
- Trains and light rail
- Real estate signs
- Point of purchase
- Outdoor advertising
- Indoor advertising
- Floor graphics

Physical characteristics

General

Calliper, face film	ISO 534	90 micron
Calliper, face film & adhesive	ISO 534	115 microns
Dimensional stability		0.76 mm max
Opacity	ISO 2471	98%
Gloss	Hunter Gloss @ 60°	86
Adhesion, initial	FINAT FTM-1, stainless steel	150 N/m
Adhesion, ultimate	FINAT FTM-1, stainless steel	200 N/m
Flammability	AS/NZS 3837:1998 ISO 5660-1:2002	Group 1 Group 1
Shelf life	Stored at 22° C/50-55 % RH	1 year
Durability **	Vertical exposure	Up to 3 years unprinted

Thermal

Application temperature	Minimum: 5°C
Temperature range	- 20°C to + 80°C

Chemical

Resistant to most petroleum based oils, greases and aliphatic solvents

Resistant to most mild acids, alkalies, and salts

Important

Information on physical characteristics is based upon tests we believe to be reliable. The values listed herein are typical values and are not for use in specifications.

They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of any material for their specific use.

All technical data is subject to change without prior notice.

Warranty

Avery Dennison® materials are manufactured under careful quality control and are warranted to be free from defect in material and workmanship. Any material shown to our satisfaction to be defective at the time of sale will be replaced without charge. Our aggregate liability to the purchaser shall in no circumstances exceed the cost of the defective materials supplied. No salesman, representative or agent is authorised to give guarantee, warranty, or make any representation contrary to the foregoing.

All Avery Dennison® materials are sold subject to the above conditions, being part of our standard conditions of sale, a copy of which is available on request.

**Expected Durability

The expected durability of Avery Dennison films are defined as the expected performance life of the Avery Dennison graphic film(s) within Zone 1 of the Avery Dennison zone system, in outdoor vertical exposure conditions.

The actual performance life will depend on a variety of factors, including selection and preparation of substrate, angle and direction of exposure, application methods, environmental conditions and cleaning/maintenance of the films. In case of films used in areas of high temperatures or humidity, high altitudes and industrially polluted areas the performance will be further reduced.

Expected Durability and Warranted Period Definitions

Expected durability is the expected period of time defined in the product data sheet, the product should, but is not warranted to, perform satisfactorily when applied in vertical exposure conditions as defined in Instructional Bulletin 1.30. The warranted period as defined in the appropriate ICS Performance Guarantee Bulletin, is the maximum period of time Avery Dennison will warrant the finished products performance in accordance with ICS Performance Guarantee Terms and Conditions 1.0, provided that the film is properly stored, converted and installed in accordance with Avery Dennison guidelines.

Test Methods

Dimensional stability:

Is measured on a 150 x 150 mm aluminium panel to which a specimen has been applied; 72 hours after application the panel is exposed for 48 hours to + 70°C, after which the shrinkage is measured.

Adhesion:

(FTM-1, FINAT) is measured by peeling a specimen at a 180° angle from a stainless steel or float glass panel, 24 hours after the specimen has been applied under standardised conditions. Initial adhesion is measured 20 minutes after application of the specimen.

Flammability:

A specimen applied to aluminium is subjected to the flame of a gas burner for 15 seconds. The film should stop burning within 15 seconds after removal from the flame.

Temperature range:

A specimen applied to stainless steel is exposed at high and low temperatures and brought back to room temperature. 1 hour after exposure the specimen is examined for any deterioration. Note: Prolonged exposure to high and low temperatures in the presence of chemicals such as solvents, acids, dyes, etc. may eventually cause deterioration.

Chemical Resistance:

All chemical tests are conducted with test panels to which a specimen has been applied. 72 hours after application the panels are immersed in the test fluid for the given test period. 1 hour after removing the panel from the fluid, the specimen is examined for any deterioration.

Corrosion Resistance:

A specimen applied to aluminium is exposed to saline mist (5% salt) at 35°C. After exposure, the film is removed and the panel is examined for traces of corrosion.