PRODUCT DATA SHEET

Avery Dennison® DOL 1400 Z Series

Issued: 03/2025

Introduction

Avery Dennison DOL 1400 Z series cast overlaminates are premium quality, ultra-flexible films designed to be used as protective overlaminate films for digitally printed images.

The films offer exceptional value for applications requiring enhanced colours and durability. Avery Dennison DOL 1400 Z series overlaminate films have specially been developed to be used for vehicle graphics.

Due to the films' excellent durability and supreme conformability, these overlaminates are highly recommended for use with Avery Dennison MPI cast media for applications on rivets and corrugations and/or for prolonged outdoor use.



Face Film

Premium quality 30 micron clear cast vinyl

DOL 1460 Z Gloss DOL 1470 Z Lustre DOL 1480 Z Matt



Adhesive

Permanent, acrylic based



Backing

DOL 1460 Z Gloss & DOL 1480 Z Matt: White bleached kraft paper, 90 g/m2 DOL 1470 Z Lustre: White bleached kraft paper, 130 g/m2



Durability

6 years

Conversion

For processing tips and reference guides please refer to Technical Bulletins:



Shelf Life

2 years

- 5.3 Recommended combinations of Avery Dennison overlaminates and Avery Dennison Digital Print Media
- » 5.4 Processing tips for Avery Dennison DOL films

Recommendations

Protective overlaminate film for digital printed images for indoor and outdoor use. Avery Dennison DOL 1400 Z series cast overlaminates can be used in combination with Avery Dennison MPI cast media for application on corrugated or riveted surfaces.

- » Vehicle graphics and vehicle wrapping
- » Interior & exterior signs
- Durable promotional and point of sale advertising
- » All permanent applications requiring excellent conformability

Features

- » Premium quality, ultra-flexible, cast vinyl
- » DOL 1460 Z Gloss enhances image colours
- » Smooth, low glare matt finish with DOL 1480 Z Matt
- » NEW Lustre DOL 1470 Z for more customisation choices
- » Protects against UV radiation and abrasion
- Excellent conformability to irregular substrates in combination with MPI cast media



Physical Characteristics

	Test method ¹	Results
Product		
Caliper, facefilm (micron)	ISO 534	30
Caliper, facefilm + adhesive (micron)	ISO 534	50
Gloss (GU)		
DOL 1460 Z Gloss	ISO 2813, 20°	70
DOL 1470 Z Lustre	ISO 2813, 60°	30
DOL 1480 Z Matt	ISO 2813, 80°	20
Dimensional stability (mm max.)	FINAT FTM 14	0.2
Shelf life (years)	Stored at 22° C/50-55 % RH	2
Durability ² (years)	Vertical exposure	6
Fire Classification Rating	EN 13501-1	B-s1, d0
Adhesive		
Adhesion, initial (N/m)	FINAT FTM-1, stainless steel	400
Adhesion, after 24 hours (N/m)	FINAT FTM-1, stainless steel	500
Temperature range		
Application temperature (min °C)		see TB 5.4
Service temperature (°C to +°C)		-40 - +80
Chemical properties ³		
Chemical resistance	Mild acids	No effect
Solvent resistance	Mild alkalis	No effect
Solvent resistance	Applied to aluminium	No effect exposed to: oils, greases, aliphatic solvents, motor oils, heptane, kerosene and JP-4 fuel.

Important

Information on physical and chemical characteristics and values in this document are based upon tests we believe to be reliable and do not constitute a warranty. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of this material to their specific use.

All technical data are subject to change. In case of any ambiguities or differences between the English and foreign versions of this document, the English version shall be prevailing and leading.

- 1) Test methods: More information about our test methods can be found on our website.
- 2) Durability: The durability is based on middle European exposure conditions. Actual performance life will depend on substrate preparation, exposure conditions and maintenance of the marking. For instance, in the case of signs facing south; in areas of long high temperature exposure such as southern European countries; in industrially polluted areas or high altitudes, exterior performance will be decreased.
- 3) Prolonged immersion in gasoline and similar fluids is not recommended.

Avery Dennison warrants that its Products meet its specifications. Avery Dennison gives no other express or implied guarantees or warranties with respect to the Products, including, but not limited to, any implied warranties of merchantability, fitness for any particular use and/or non infringement. All Avery Dennison products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purposes. The period of warranty is one (1) year from the date of shipment unless expressly provided otherwise in the product data sheet. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see http://terms.europe.averydennison.com.

Avery Dennison's aggregate liability to Purchaser, whether for negligence, breach of contract, misrepresentation or otherwise, shall in no circumstances exceed the price of the defective, non-conforming, damaged or undelivered Products which give rise to such liability as determined by net price invoices to Purchaser in respect of any occurrence or series of occurrences. In no circumstances shall Avery Dennison be liable to Purchaser for any indirect, incidental or consequential loss, damage or injury, including without limitation, loss of anticipated profits, goodwill, reputation, or losses or expenses resulting from third party claims.

© 2025 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.

