## PRODUCT DATA SHEET

# **Avery Dennison®** 700PF Premium Film

Issued: 11/2024

#### Introduction

Conversion

printed.

Avery Dennison® 700 Premium Films are ideal for many medium-life indoor and outdoor applications with an excellent dimensional stability. Avery Dennison® 700 Premium Films are available in a very extensive range of standard colours. Any other colour can be ordered through our extended colour match services. The embossed backing of the Easy Apply version is providing enhanced ease-of-use during application. Entrapped air can easily be rubbed out without the need to punch the vinyl film.

Avery Dennison® 700 Premium Films can be cut on a

Dennison® 700 Premium Films can be thermal transfer

The Hi-Tack version is suitable for difficult to adhere to

surfaces such as low surface energy substrates (eg.

HDPE or PP) and matt interior painted walls.

wide variety of computerised sign cutting equipment.

Die cutting will also show good performance. Avery



#### **Face Film**

64 micron polymeric vinyl film



#### **Adhesive**

permanent, acrylic based

Hi-tack, permanent acrylic based; designed for low-surface energy substrates

#### **Backing**



One side coated bleached kraft paper, 135 a/m<sup>2</sup>

Two-side polyethylene coated kraft paper, 140 g/m² with Easy Apply Technology



#### **Durability**

Up to 8 years outdoor (vertical exposure)



#### **Shelf Life**

2 years - stored at 22°C/50% RH

Do NOT use wet application methods for Avery Dennison® 700 Premium Easy Apply version.

#### Recommendations

Avery Dennison® 700 Premium Films offer a very wide range of special colours for:

- » Window graphics
- » Directional signage, indoor and outdoor
- » Vehicle graphics, rigid sided
- » Poster sites
- » Promotional displays

Application surfaces may vary from regular flat to curved substrates for which a medium-term durability is required.

#### **Features**

- Attractive film range with 100 colours all REACH compliant
- » High gloss appearance
- » Excellent dimensional stability
- Superior cutting and weeding
- Sood opacity
- Blue contrast backing paper on Avery Dennison® 700 PF White and 730 PF White Matt
- » New liner imprint design with square pattern to support manual conversion
- » Available with Easy Apply Technology, for an easy application
- » Hi-Tack version: outstanding adhesion to low energy surfaces, like PP and PE substrates
- » Fire certification EN13501-1+A1:2013, B-s1, d0





### **Physical Characteristics**

| Triyologi Origination                  |                                    | Danulta                                |                      |                 |
|--|------------------------------------|--|----------------------|-----------------|
| 5                                      | Test method <sup>1</sup>           | Results                                |                      |                 |
| Product                                |                                    |  |                      |                 |
| Caliper, facefilm (micron)             | ISO 534                            | 64                                     |                      |                 |
| Caliper, facefilm + adhesive (micron)  | ISO 534                            | 85                                     |                      |                 |
| Gloss (GU)                             | ISO 2813                           | Gloss 20° 50                           |                      |                 |
|  |                                    | Matt 85° 20                            |                      |                 |
| Dimensional stability (mm max.)        | DIN 30646                          | 0.25                                   |                      |                 |
| Floraction (9/)                        | DIN 52455                          | 120                                    |                      |                 |
| Elongation (%)                         | DIN 53455                          |  |                      |                 |
| Flammability                           |                                    | Self-extinguishing                     |                      |                 |
| Accelerated ageing                     | SAE J 1960, 2000h<br>exposure      | No negative impact on film performance |                      |                 |
| Shelf life                             | 2 years- stored at<br>22°C/ 50% RH | stored at 22°C/ 50% RH                 |                      |                 |
| Durability <sup>2</sup>                | Vertical exposure                  |  |                      |                 |
|  | White & Black                      | 8 years                                |                      |                 |
|  | Colors & Clear                     | 7 years                                |                      |                 |
|  | Metallics                          | 5 years                                |                      |                 |
| Adhesive                               | Metallics                          | Kraft version                          | Facus Annius service | Hi Taak yaraian |
|  |                                    |  | Easy Apply version   | Hi-Tack version |
| Adhesion, initial (N/m)                | FINAT FTM-1,<br>stainless steel    | 400                                    | 400                  |                 |
| Adhesion, after 24 hours (N/m)         | FINAT FTM-1,<br>stainless steel    | 500                                    | 500                  |                 |
| Adhesion, initial (N/m)                | FINAT FTM-1, HDPE                  |  |                      | 520             |
| Adhesion, after 24 hours (N/m)         | FINAT FTM-1, HDPE                  |  |                      | 530             |
| Temperature range                      |                                    |  |                      |                 |
| Application                            |                                    | +10                                    |                      |                 |
| temperature<br>(Minimum: °C)           |                                    | 110                                    |                      |                 |
| Service temperature (°C to +°C)        |                                    | -40 to +90                             |                      |                 |
| Chemical properties <sup>2</sup>       |                                    |  |                      |                 |
| Humidity resistance                    | 200 hours exposure                 | No effect                              |                      |                 |
| Water resistance                       | 24 hours immersion                 | No effect                              |                      |                 |
| Detergent (1% solution)                | 24 hours immersion                 | No effect                              |                      |                 |
| Detergent solution<br>65°C             | 8 hours immersion                  | No effect                              |                      |                 |
| Isopropylic Alcohol /<br>Water (20/80) | 10 minutes immersion               | No effect                              |                      |                 |
|  |                                    |  |                      |                 |



#### **Important**

Information on physical and chemical characteristics and values in this document are based upon tests we believe to be reliable and do not constitute a warranty. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of this material to their specific use.

All technical data are subject to change. In case of any ambiguities or differences between the English and foreign versions of this document, the English version shall be prevailing and leading.

- 1) Test methods: More information about our test methods can be found on our website.
- 2) Prolonged immersion in gasoline and similar fluids is not recommended.

Avery Dennison warrants that its Products meet its specifications. Avery Dennison gives no other express or implied guarantees or warranties with respect to the Products, including, but not limited to, any implied warranties of merchantability, fitness for any particular use and/or non infringement. All Avery Dennison products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purposes. The period of warranty is one (1) year from the date of shipment unless expressly provided otherwise in the product data sheet. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <a href="http://terms.europe.averydennison.com">http://terms.europe.averydennison.com</a>.

Avery Dennison's aggregate liability to Purchaser, whether for negligence, breach of contract, misrepresentation or otherwise, shall in no circumstances exceed the price of the defective, non-conforming, damaged or undelivered Products which give rise to such liability as determined by net price invoices to Purchaser in respect of any occurrence or series of occurrences. In no circumstances shall Avery Dennison be liable to Purchaser for any indirect, incidental or consequential loss, damage or injury, including without limitation, loss of anticipated profits, goodwill, reputation, or losses or expenses resulting from third party claims.

© 2024 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.

