

# PRODUCT DATA SHEET

## Avery Dennison<sup>®</sup> MPI 2150<sup>™</sup> Translucent

Issued: 04/2023

### Introduction

Avery Dennison Multi Purpose Inkjet 2150 is a lustre white translucent PVC film with a permanent adhesive, recommended for use on flat to slightly curved surfaces.

### Conversion

Avery Dennison MPI 2150 is a multi-purpose vinyl, developed for use on various super wide format printers using solvent-, eco/mild solvent-, UV curable and latex inks.

To enhance colour and protect images against UV radiation and abrasion, Avery Dennison MPI 2150 is recommended to be overlaminated with Avery Dennison DOL 2400 series.

### Recommendations

- » Graphics for internally illuminated signs.
- » Window decorations and graphics.

### Features

- » Excellent printability and handling on selected printers.
- » Easy conversion because of dimensionally stable special backing.
- » Excellent colour uniformity in reflected and transmitted light.
- » Excellent durability.
- » Excellent adhesion.

\*The durability of a printed image always depends on the toner/ink, film, used overlaminate, processing and exposure conditions



#### Face Film

80 micron white translucent PVC film.



#### Adhesive

Permanent, clear acrylic based.



#### Backing

Two sides polyethylene coated kraft paper, 140g/m<sup>2</sup>.



#### Durability

7 years



#### Shelf Life

2 years

## Physical Characteristics

Features	Test method <sup>1</sup>	Results
Caliper, facefilm	ISO 534	80 micron
Caliper, facefilm + adhesive	ISO 534	115 micron
Dimensional stability	FINAT FTM 14	0.3 mm max.
Gloss	ISO 2813, 20	15
Adhesion, initial	FINAT FTM-1, stainless steel	560
Adhesion, ultimate (N/m)	FINAT FTM-1, stainless steel	800
	PMMA	900
	Glass	860
	Polystyrene	900
Flammability	EN 13501-1	B-s1,d0
Shelf life	Stored at 230°C/50-55% RH	2 years
Durability	Vertical exposure	7 years

Temperature range	Test method <sup>1</sup>	Results
Min. application temperature		≥ +10°C
Service temperature		-50°C to +110°C
Heat resistance	3 weeks exposure at 80 °C	No negative impact on film Performance

**NOTE:** Materials have to be properly dried before further processing, for example laminating, varnishing or application. The residual solvents could change the products' specific features.

For good print and converting result we recommend to let the rolls acclimatize in the print/lamination room at least 24h. before printing or converting. Too much temperature or humidity deviation between material and room climate can cause layflatness and/or printability issues.

Generally, constant material storage conditions of ideally 20°C (+/-2°C) /50% RH (+/- 5%), without too big climate deviations, will support a more robust and stable printing/converting process. For further details, please refer to TB 1.11.

## Important

Information on physical and chemical characteristics and values in this document are based upon tests we believe to be reliable and do not constitute a warranty. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of this material to their specific use.

All technical data are subject to change. In case of any ambiguities or differences between the English and foreign versions of this document, the English version shall be prevailing and leading.

1) Test methods: More information about our test methods can be found on our website.

*Avery Dennison warrants that its Products meet its specifications. Avery Dennison gives no other express or implied guarantees or warranties with respect to the Products, including, but not limited to, any implied warranties of merchantability, fitness for any particular use and/or non infringement. All Avery Dennison products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purposes. The period of warranty is one (1) year from the date of shipment unless expressly provided otherwise in the product data sheet. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>.*

*Avery Dennison's aggregate liability to Purchaser, whether for negligence, breach of contract, misrepresentation or otherwise, shall in no circumstances exceed the price of the defective, non-conforming, damaged or undelivered Products which give rise to such liability as determined by net price invoices to Purchaser in respect of any occurrence or series of occurrences. In no circumstances shall Avery Dennison be liable to Purchaser for any indirect, incidental or consequential loss, damage or injury, including without limitation, loss of anticipated profits, goodwill, reputation, or losses or expenses resulting from third party claims.*

*© 2023 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.*